

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

LOGLO

Technical Specifications

Vehicle Type	Medium Oil Alkyd
Solvent	Turpentine
Enviro Rating	Flammable
Dilution / Thinning	Supplied ready for use but may be thinned with Turpentine
Theoretical Spread Rate	10m ² per litre
Apply with	Brush, Roller or Spray
Drying time	Surface Dry: 1 hour Hard Dry: 5 hours
Wash ability	Good
Elongation	Pass
Pigment	Pigmented
Solids Volume	42%
Flexibility	Fair
Colour	White and colours of your choice
Finish	Egg Shell
Storage	Cool, dry place.
Over coating	N/A
Packaging	1L, 5L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Good
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable (see Material Safety Data sheet)
Catalyst Ratio	N/A
Recommended Dry Film	35 - 40 microns
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	White Alkyd paint

Note: *Loglo Egg Shell Enamel's viscosity is set at 25°C. Should temperatures decrease or better flow be required from the product, it must be thinned with Turpentine.*

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sales@paintcor.co.za

Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955

Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 CERTIFIED

